

Belt Type Cover	Nylon Type	Pressure	Splicing Solutions Polybond Type		Press Temperature		Press Time (min)
			Nylon	Rubber	(Deg F)	(Deg C)	
TTA TAIR SG KSG	250	25 psi	A	A	194-212	90-100	10
	350	25 psi	A	A	194-212	90-100	15
	500	25 psi	A	A	194-212	90-100	15
	750	25 psi	A	A	212-230	100-110	15
	1000	25 psi	A	A	212-230	110-100	15
LA	250	25 psi	A	E	194-212	90-100	15
	350	25 psi	A	E	194-212	90-100	15
	500	25 psi	A	E	212-230	100-110	20
	750	25 psi	A	E	212-230	100-110	20
	1000	25 psi	A	E	212-230	100-110	30
	1500	25 psi	A	E	212-230	100-110	30
	2000	25 psi	A	E	212-230	100-110	30
TFL	6S	25 psi	A	E	212-230	100-110	30
	7S	25 psi	A	E	212-230	100-110	30
	10S	25 psi	A	E	212-230	100-110	30
	15S	25 psi	A	E	212-230	100-110	30
	18S	25 psi	A	E	212-230	100-110	30
	3SH	25 psi	A	E	212-230	100-110	20
TFM	15S	25 psi	A	E	212-230	100-110	30
MA	250	25 psi	A	E	212-230	100-110	20
	350	25 psi	A	E	212-230	100-110	20
	500	25 psi	A	E	212-230	100-110	20
	750	25 psi	A	E	212-230	100-110	30
	1000	25 psi	A	E	212-230	100-110	30
	1500	25 psi	A	E	212-230	100-110	30
	2000	25 psi	A	E	212-230	100-110	30
HA	500	25 psi	A	E	212-230	100-110	30
	750	25 psi	A	E	212-230	100-110	30
	1000	25 psi	A	E	212-230	100-110	30
	1500	25 psi	A	E	212-230	100-110	30
	2000	25 psi	A	E	212-230	100-110	30
XH	500-3	25 psi	A	E	212-230	100-110	30
	500-4	25 psi	A	E	212-230	100-110	30
	500-5	25 psi	A	E	212-230	100-110	30
	500-6	25 psi	A	E	212-230	100-110	30
	750-6	25 psi	A	E	212-230	100-110	30
MH	3000	25 psi	A	E	212-230	100-110	30
	4000	25 psi	A	E	212-230	100-110	30

*Note: 25psi= 200kPa

For specific belt types conditions and instructions, please contact your sales rep or Nitta's technical department. Please contact Nitta with any questions.